

| | | | |
|------------------------|---|-------------------------|----------------|
| Client: | Curoil N.V. | Date Sampled : | April 22, 2024 |
| Job Location: | Emmastad | Date Submitted : | April 22, 2024 |
| Product: | Premium Unleaded Gasoline | Date Tested : | April 22, 2024 |
| Product source: | Shore Tank 0670 After discharge Vessel MT Amirante | Date Issued : | April 22, 2024 |

Sample Description : Average Composite

| Test | Method | Specification | | Results | Units |
|-----------------------------|------------|----------------|---------|----------------|----------|
| | | Minimum | Maximum | | |
| Specific Gravity at 60/60°F | ASTM D4052 | | | 0.7535 | |
| API at 60°F | ASTM D4052 | Report | | 56.3 | Degrees |
| Density at 15°C | ASTM D4052 | 720.0 | 775.0 | 753.2 | kg/m3 |
| Appearance | Visual | Clear & Bright | | Clear & Bright | |
| Copper Strip 3 Hr/50°C | ASTM D130 | | 1 | 1A | |
| Distillation | ASTM D86 | | | | |
| Distillation IBP | ASTM D86 | 30 | | 34.4 | °C |
| Distillation 10% Recovered | ASTM D86 | 40 | 70 | 55.4 | °C |
| Distillation 50% Recovered | ASTM D86 | 80 | 115 | 94.8 | °C |
| Distillation 90% Recovered | ASTM D86 | | 180 | 159.5 | °C |
| Distillation FBP | ASTM D86 | | 215 | 190.4 | °C |
| Distillation Residue | ASTM D664 | | 2 | 1.1 | %vol |
| Evaporated @70°C | ASTM D86 | Report | | 26.6 | %vol |
| Existent Gum | ASTM D381 | | 4.0 | <0.5 | mg/100ml |
| Antiknock Index (R+M/2) | CALC | Report | | 91 | O.N. |
| Motor Octane Number | ASTM D2700 | 85.0 | | 86.0 | M.O.N. |
| Research Octane Number | ASTM D2699 | 95.0 | | 95.9 | R.O.N. |
| Aromatic Content | ASTM D1319 | | 35.0 | 35.0 | %vol |
| Olefines Content | ASTM D1319 | | 18.0 | 9.0 | %vol |
| Olefines and Aromatics | ASTM D1319 | | 45.0 | 44.3 | %v |
| Water Content | ASTM D6304 | Report | | 637 | mg/Kg |
| Oxidation Stability | ASTM D525 | 360 | | >360 | min |
| Reid Vapor Pressure @ 100F | ASTM D5191 | | 8.7 | 8.66 | psi |
| Mercaptan Sulphur | ASTM D3227 | | 0.0015 | 0.0006 | %m |
| Odor | | Marketable | | Marketable | |
| Comment | | | | | |

The issuance of this document does not exonerate any party from exercising all their rights and discharging all their liabilities under any contract of Sale. Stipulations to the contrary are not binding upon Intertek Oil, Chemical & Agri. Intertek Oil, Chemical & Agri responsibility is limited to gross negligence proven, and will in no case be more than ten times any fees or commission. All activities are undertaken based on the applicable Intertek Oil, Chemical & Agri Terms and Conditions of Service. No should attempt to use or rely upon the contents of this document without having read and understood the Terms and Conditions applicable thereto. A copy can be obtained at <http://www.intertek.com/terms>.

"The analysis results were performed by CRU Refinery Lab.
"Intertek cannot accept liability for the accuracy of any results not performed by its own laboratories."



For Intertek Curacao _____

Glenn Gustina
Branch Coordinator

