intertek
caleb brett

Report of Analysis

Curacao Oil N. V. (Curoil)
Excon Martina
A.M Chumanceiro Blvd.15,
P.O. Box 3927
Willemstad
Netherlands Antilles

Our Reference Number: NA100-0008684
Lab Reference Number: 2026-CURA-000065
Customer Reference Number: MT Portola

Customer Product Description: ULSD
Location: Prins Hendrik Wharf, Curacao, , Netherlands Antilles
Sample Representing: Shore Tank 06 U,M,L, Average After Discharge
Drawn By: Intertek

Sample ID: 2026-CURA-000065-002
Date Sampled: 16-Apr-2026
Date Submitted: 16-Apr-2026
Date Tested: 04-May-2026

	Method	Property	Result	Units	Min	Max	P/F
	ASTM D445	Kinematic Viscosity at 40 °C	2.338	mm²/s	2.0	4.1	Pass
	ASTM D4052	API Gravity @ 60°F	38.7	°API	32.0		Pass
		Density @ 15°C	830.9	kg/m³	820	845	Pass
		Specific Gravity @ 60°F	0.8313				
	ASTM D976	Cetane Index	50.4		46.0		Pass
	ASTM D2622	Sulfur Content	7.7	ppm Wt		15	Pass
	ASTM D93	Corrected Flash Point	64.5	°C	60.0		Pass
	ASTM D664	Acid Number	0.03	mg KOH/g		0.50	Pass
2	ASTM D2274	Total Insolubles (Oxidation Stability)	1	mg/L		25	Pass
	ASTM D4530	Micro Method Carbon Residue 10% Distillation Residue	<0.1	Wt %		0.3	Pass
	ASTM D2500	Cloud Point	-10	°C			
	ASTM D97	Pour Point	-24	°C		0	Pass
	ASTM D4176 MOD	Appearance	Clear & Bright		Clear and Bright		Pass
	ASTM D482	Ash	<0.010	Wt %		0.010	Pass
	ASTM D6079	Major Axis	420	µm			
		Minor Axis	360	µm			
		Wear Scar Diameter	390	µm		460	Pass
	ASTM D86	Initial Boiling Point	168.0	°C			
		10% Recovery	199.0	°C			
		50% Recovery	253.0	°C		288.0	Pass
		90% Recovery	322.0	°C	282.0	338.0	Pass
		Final Boiling Point	355.0	°C			
		Residue	1.0	% Vol		2.0	Pass
		Loss	1.0	% Vol		2.0	Pass
	ASTM D1500	ASTM Color	<1		<= 2.5		Pass
2	ASTM D130	Copper Corrosion @ 50°C (122°F)/3 hr	1a		Max No. 3		Pass
2	ASTM D1319	Aromatics	25.8	Vol %		35.0	Pass
2	EN 12662	Total Contamination	<12.0	mg/kg		24.0	Pass
2	ASTM D7111	Silicon	<0.10	mg/kg			
	ASTM D2624	Temperature	24.0	°C			
		Electrical Conductivity	222	pS/m	25		Pass
	ASTM D95	Water Content	<0.01	Vol %		0.02	Pass
2	ASTM D6890	Derived Cetane Number (DCN)	53.9				
2	EN 12916	Polycyclic Aromatic Hydrocarbons (Proc A)	2.2	%(m/m)			

intertek
caleb brett

Report of Analysis

Our Reference Number: NA100-0008684
Lab Reference Number: 2026-CURA-000065
Customer Reference Number: MT Portola

Customer Product Description: ULSD
Location: Prins Hendrik Wharf, Curacao, , Netherlands Antilles
Sample Representing: Shore Tank 06 U,M,L, Average After Discharge
Drawn By: Intertek

Sample ID: 2026-CURA-000065-002
Date Sampled: 16-Apr-2026
Date Submitted: 16-Apr-2026
Date Tested: 04-May-2026

	Method	Property	Result	Units	Min	Max	P/F
2	EN 16576	Manganese Content	<1.0	mg/L			
2	ASTM D7359	Total Chlorine	<1.0	mg/kg			

Material conforms to the Curoil ULSD requirements on above relevant point(s) of testing.

The issuance of this document does not exonerate any party from exercising all their rights and discharging all their liabilities under any contract of Sale. Stipulations to the contrary are not binding upon Intertek Oil, Chemical & Agri. Intertek Oil, Chemical & Agri responsibility is limited to gross negligence proven, and will in no case be more than ten times any fees or commission. All activities are undertaken on the basis of the applicable Intertek Oil, Chemical & Agri Terms and Conditions of Service. Nor should attempt to use or rely upon the contents of this document without having read and understood the Terms and Conditions applicable thereto. A copy can be obtained at http://www.intertek.com/terms.

Results are only representative of the sample tested. All tests have been performed using the latest version unless otherwise indicated. This report shall not be reproduced except in full without written approval of Intertek. Report is subject to our standard Terms and Conditions which can be obtained at our website : http://www.intertek.com/terms

The analysis results denoted by (2) were performed by Intertek Laboratory Suriname

Signed: _____ Date: 04-May-2026

Glenn Gustina, Branch Coordinator